

swissporPIR Alu

Description PIR insulation panel
 Surface Aluminium coating on both sides
 Application Method Glued or mechanically fixed
 Product norm EN 13165:2012 + A2:2016

Born in the  Alps

Technical Data

Specifications	Test method	Unit	Requirement
Length ¹⁾	EN 822	[mm]	1200
Width ¹⁾	EN 822	[mm]	600
Apparent density (ρ) ²⁾	EN 1602	[kg/m ³]	~ 30
Thickness	EN 823	[mm]	20 - 300
Thermal conductivity (λ_D)	EN 12667	[W/(m·K)]	0.022
Thermal capacity (c)		[Wh/(kg·K)]	0.39
Resistance to vapour diffusion (μ)	EN 12086		~ watertight
Compressive strength (σ_{10})	EN 826	[kPa]	≥ 150
Compressive creep (50 years, <2%) (σ_c)	EN 1606	[kPa]	25
Reaction to fire	EN 13501-1		E
Maximum packing height (including pallet / spacer)		[mm]	2700
Height of pallet / spacer		[mm]	100
Packaging system			Stretch film (PE)

¹⁾ Useful dimensions

²⁾ Apparent density does not represent an essential characteristic according to the norms SN EN 13165 / SIA 279.165.

Packaging

Thickness [mm]	20	30	40	50	60	70	80	100	120	140	160	180	200	220	240	260	280	300
m ² / pack	14,40	11,52	8,64	7,20	5,76	4,32	4,32	3,60	2,88	2,16	2,16	2,16	1,44	1,44	1,44	1,44	0,72	0,72

Safety: Material Safety Data Sheets are available upon request at the under mentioned mail address of the Team Export.

Storage: The material has to be stored in a dry covered place and it is advisable not to exceed 12 months of storage. Protect the product from extremely low temperatures. During storage avoid exposure to direct sunlight.

Application: For a correct use of the products, refer to the specific technical documents issued by swisspor Romandie SA anyway the customer is responsible for ensuring that each product is suitable for its intended purpose and that the condition of use are suitable. If any law, norm or regulation different from what declared by the manufacturer is in force in the Country where the product must be installed, this must be considered as compulsory by the applicator and it is his own responsibility to follow the suitable legislative references.

Disclaimer: swisspor Romandie SA pursues a policy of constant product development and information contained in this document that is therefore subject to change without notice.

swisspor Romandie SA
 Ch. du Bugnon 100 – CP 60
 1618 Châtel-Saint-Denis
 Tel. +41 21 948 48 48
 Fax: +41 21 948 48 49
 romandie@swisspor.com
 www.swisspor.ch

swisspor Romandie SA
 Export Team
 1618 Châtel-Saint-Denis
 Tel. +41 21 948 48 48
 Fax: +41 21 948 48 19
 export@swisspor.com
 www.swisspor.ch



swissporPIR Alu

High performance insulation panel made of polyisocyanurate (PIR)

swissporPIR Alu panels guarantee an optimum, economical thermal insulation of roofs, walls and floors.

Both sides are covered with an **aluminium foil watertight to vapour.**

Made without halogen, its use **protects the environment and human health.**

Structure

PIR insulation panel, aluminium coating on both sides.

Battered available from 50 mm.

