

swissporPIR Premium

Description	PIR insulation panel
Surface	Aluminium coating on both sides
Application Method	Glued or mechanically fixed
Product norm	EN 13165:2012 + A2:2016

Born in the  Alps



Technical Data

Specifications	Test method	Unit	Requirement
Length ¹⁾	EN 822	[mm]	1200
Width ¹⁾	EN 822	[mm]	600
Apparent density (ρ) ²⁾	EN 1602	[kg/m ³]	~ 30
Thickness	EN 823	[mm]	20 - 240
Thermal conductivity (λ_D)	EN 12667	[W/(m·K)]	0.020
Thermal capacity (c)		[Wh/(kg·K)]	0.39
Resistance to vapour diffusion (μ)	EN 12086		~ watertight
Compressive strength (σ_{10})	EN 826	[kPa]	≥ 120
Compressive creep (50 years, <2%) (σ_c)	EN 1606	[kPa]	25
Reaction to fire	EN 13501-1		E
Maximum packing height (including pallet / spacer)		[mm]	2700
Height of pallet / spacer		[mm]	100
Packaging system			Stretch film (PE)

¹⁾ Useful dimensions

²⁾ Apparent density does not represent an essential characteristic according to the normes SN EN 13165 / SIA 279.165

Packaging

Thickness [mm]	20	30	40	50	60	70	80	100	120	140	160	180	200	220	240
m ² / pack	14.4	11.52	8.64	7.20	5.76	4.32	4.32	3.60	2.88	2.16	2.16	2.16	1.44	1.44	1.44

Safety: Material Safety Data Sheets are available upon request at the under mentioned mail address of the Team Export.

Storage: The material has to be stored in a dry covered place and it is advisable not to exceed 12 months of storage. Protect the product from extremely low temperatures. During storage avoid exposure to direct sunlight.

Application: For a correct use of the products, refer to the specific technical documents issued by swisspor Romandie SA anyway the customer is responsible for ensuring that each product is suitable for its intended purpose and that the condition of use are suitable. If any law, norm or regulation different from what declared by the manufacturer is in force in the Country where the product must be installed, this must be considered as compulsory by the applicator and it is his own responsibility to follow the suitable legislative references.

Disclaimer: swisspor Romandie SA pursues a policy of constant product development and information contained in this document that is therefore subject to change without notice.

swisspor Romandie SA
 Ch. du Bugnon 100 – CP 60
 1618 Châtel-Saint-Denis
 Tel. +41 21 948 48 48
 Fax: +41 21 948 48 49
 export@swisspor.com
 www.swisspor.ch



swisspor
 saving energy

swissporPIR Premium

High performance insulation panel made of polyisocyanurate (PIR), with low Global Warming Potential (GWP). Its exceptional insulation power allows very thin panels to bring a satisfying insulation on pitched or flat roofs, floors, walls and screeds.

Both sides are covered with an **aluminium foil resistant to vapour diffusion**.

Made without halogens, its use **protects the environment and human health**.

Structure

PIR insulation panel, aluminium coating on both sides.

Battered available from 50 mm.

