

swissporBIKUTOP LL RENO BLACK

Located in the heart of the Swiss Alps, our research and development team created swissporBIKUTOP LL RENO BLACK to be applied as a **capsheet** when **refurbishing** a flat roof. Its reinforcement, in polyester, has been chosen by our experts to **meet the most demanding expectations**.

This built-in vapour dispersion system prevents the formation of blisters that could appear when refurbishing a roof waterproofing system.

This membrane offers the most effective and secure way to refurbish a roof.

Our choices of materials and our processes make our products **setting the standards of quality and sustainability in the waterproofing industry.**



Upper surface: Slate black



Lower Surface: RENO System

swissporBIKUTOP LL RENO BLACK

Description	SBS modified bituminous membrane
Surface	Upper Slate (black)
	Lower Thermofusible film
Reinforcement	Polyester
Application Method	Torched
Rolls / pallet (m ² / Pallet)	15 (115.5)
Application norm	EN 13707

Born in the  Alps



Technical Data

Characteristic	Test method	Unit	Value
Length	EN 1848-1	[m]	7.00
Width	EN 1848-1	[m]	1.10
Nominal weight of the product	EN 1849-1	[kg/m ²]	6.00 ¹⁾
Thickness	EN 1849-1	[mm]	5.30 ¹⁾
Visible defects	EN 1850-1		None
Straightness	EN 1848-1	[mm/10m]	≤ 20
Flexibility at low temperature	EN 1109	[°C]	≤ -20
Flow resistance at elevated temperature	EN 1110	[°C]	≥ 110
Maximum tensile force	EN 12311-1	[N/50 mm]	long.: 850 ²⁾ transv.: 600 ²⁾
Elongation	EN 12311-1	%	long.: 35 ²⁾ transv.: 35 ²⁾
Dimensional stability	EN 1107-1	%	≤ 0.5
Artificial aging behavior at low temperature flexing	EN 1296	[°C]	≤ -15 ⁴⁾
Artificial aging creep resistance at elevated temperature	EN 1296	[°C]	≥ 100 ³⁾
Reaction to fire	EN 13501-1	-	E
Watertightness	EN 1928 meth. B	-	Passed at 200 kPa/24h (Typ T)
Resistance to static loading	EN 12730	[kg]	≥ 20
Resistance to impact	EN 12691	[mm]	1250
Diffusion equivalent air layer thickness s=μ•d	EN 1931	[m]	250 ³⁾
Resistance to root penetration	EN 13948	-	NPD
Adhesion of granules	EN 12039	%	≤ 30
Shear strength of the joint seam	EN 12317-1	[N/50 mm]	NPD

*NPD= No Performance Determinated

¹⁾ Tolerance ± 10%

²⁾ Tolerance ± 15%

³⁾ Tolerance - 15%

⁴⁾ Tolerance + 10°C

⁵⁾ Tolerance -10°C

Safety: Material Safety Data Sheets are available upon request at the under mentioned mail address of the Team Export.

Storage: The material has to be stored in a dry covered place, vertically on pallets or on flat surfaces, less than 12 months (6 months in case of self-adhesive membranes). Protect the membrane from extremely low temperatures and condition the material at temperature above +5 °C at least 24 hours before installation. During storage avoid exposure to direct sunlight.

Application: For a correct use of the products, refer to the specific technical documents issued by swisspor Romandie SA. The customer stays responsible for ensuring that each product is suitable for its intended use and that the conditions of use are the correct ones. If any law, norm or regulation are in force in the Country of application and differs from what declared by the manufacturer, these must be considered as compulsory by the applicator and it is his own responsibility to follow it.

Disclaimer: swisspor Romandie SA pursues a policy of constant product development and information contained in this document that is therefore subject to change without

swisspor Romandie SA
Ch. du Bugnon 100 – CP 60
1618 Châtel-Saint-Denis
Tel. +41 21 948 48 48
Fax: +41 21 948 48 49
romandie@swisspor.com
www.swisspor.ch

swisspor Romandie SA
Export Team
1618 Châtel-Saint-Denis
Tel. +41 21 948 48 95
Fax: +41 21 948 48 19
export@swisspor.com
www.swisspor.ch



swisspor
saving energy